



Technical Data Sheet

QLE 1039

*Quantum Silicones' 40 Durometer Addition Cure
for Coating Applications*

Product Description

QLE 1039 is a 100% silicone solids elastomer designed for fabric or cloth coating applications. This two component system offers a tough coating, excellent adhesion and fast cure.

Key Features

- 100% solids – no solvents
- Long pot life
- Excellent adhesion
- Tough, resilient coating

Typical Properties

Uncatalyzed Properties

	“A” Component	“B” Component
Viscosity, cps	34,500	21,500
Appearance	Translucent	Blue
Specific Gravity, g/cm ³	1.02	1.02
Mix Ratio	1:1	

Catalyzed Properties (cured 1 hr. @ 150C)

Pot life, hours	>72
Durometer, Shore A	41
Tensile, psi	725
Elongation, %	200
100% Modulus, psi	470

Mixing

Thoroughly stir both A and B components prior to mixing together.

Mixing by hand

Combine 1 parts of A component and 1 part of B component by weight and stir until completely mixed. Use care when mixing to minimize air entrapment.

Mixing and dispensing with automatic equipment

Use properly ratioed equipment for a 1:1 mix ratio. Also use a mixing system that will properly mix A and B components. Once mixed properly the material will have >72 hour pot life.

Storage and Shelf Life

QLE 1039 should be stored in the original unopened container at 25C (77F). It will remain useful for a period of 12 months if stored under those conditions.

Not for Product Specification

The technical data listed herein are provided as a reference only and are not intended as sales specifications. For sales and technical assistance or for product recommendations, please call 1-800-852-3147.

Quantum Silicones
8021 Reycan Rd
Richmond, VA 23237
Phone (804) 271-9010 Fax (804) 271-9055
Customer Service (800)852-3147
www.quantumsilicones.com